

ENVIRONMENTAL PRODUCT DECLARATION

as per ISO 14025 and EN 15804+A2

Owner of the Declaration	Knauf Ceiling Solutions GmbH & Co. KG
Publisher	Institut Bauen und Umwelt e.V. (IBU)
Programme holder	Institut Bauen und Umwelt e.V. (IBU)
Declaration number	EPD-KNA-20250400-IBA1-EN
Issue date	13.08.2025
Valid to	12.08.2030

THERMATEX Acoustic (GR)

Knauf Ceiling Solutions GmbH & Co. KG

www.ibu-epd.com | <https://epd-online.com>



ECO PLATFORM

EPD
VERIFIED



1. General Information

Knauf Ceiling Solutions GmbH & Co. KG

Programme holder

IBU – Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

Declaration number

EPD-KNA-20250400-IBA1-EN

This declaration is based on the product category rules:

Mineral panels, 01.08.2021
(PCR checked and approved by the SVR)

Issue date

13.08.2025

Valid to

12.08.2030



Dipl.-Ing. Hans Peters
(Chairman of Institut Bauen und Umwelt e.V.)



Florian Pronold
(Managing Director Institut Bauen und Umwelt e.V.)

THERMATEX Acoustic (GR)

Owner of the declaration

Knauf Ceiling Solutions GmbH & Co. KG
Elsenthal 15
94481 Grafenau
Germany

Declared product / declared unit

1 m² of mineral ceiling tile

Scope:


This document refers to 1 m² of THERMATEX Acoustic mineral ceiling tile with a thickness of 19 mm manufactured at the production site in Grafenau, Germany.

The owner of the declaration shall be liable for the underlying information and evidence; the IBU shall not be liable with respect to manufacturer information, life cycle assessment data and evidences.

The EPD was created according to the specifications of EN 15804+A2. In the following, the standard will be simplified as *EN 15804*.

Verification

The standard EN 15804 serves as the core PCR	
Independent verification of the declaration and data according to ISO 14025:2011	
<input type="checkbox"/>	internally
<input checked="" type="checkbox"/>	externally



Manfred Russ,
(Independent verifier)

2. Product

2.1 Product description/Product definition

The ceiling tiles are manufactured using a wet-felt process and consist of biosoluble mineral wool, perlite, clay and starch. The ceiling tiles meet the requirements of *DIN 18177* and *DIN EN 13964*.

The mineral tiles are available in a wide range of different surface designs and product properties. Depending on the design, the ceiling tiles are available in different formats and edge finishes.

This EPD applies to the following product:
THERMATEX Acoustic 19 mm

For the placing on the market of the product in the European Union/European Free Trade Association (EU/EFTA) (with the exception of Switzerland) *Regulation (EU) No. 305/2011 (CPR)* applies. The product needs a declaration of performance taking into consideration *EN 13964:2014, suspended ceiling requirements and test methods* and the CE-marking. For the application and use the respective national provisions apply.

2.2 Application

Mineral tiles (wet-felt) are typically used as lay in for suspended ceiling constructions. They are primarily used as optical cladding, but also for sound absorption and sound insulation, for fire resistance and against fire spreading, for cleanrooms and high hygiene requirements.

2.3 Technical Data

Mineral boards (wet-felt) are regulated by *EN 13964* and have corresponding labelling and declaration of performance. The following data provide an overview of results:

Construction data (according to DIN 18177)

Name	Value	Unit
Thermal conductivity	0.06	W/(mK)
Sound absorption acc. ISO 354 and ISO 11654	0.65(H)	%
Airborne sound reduction acc. ISO 10848 and EN 717-1	38	dB
Gross density	263	kg/m ³

Performance data of the product in accordance with the declaration of performance with respect to its essential characteristics according to *EN 13964:2014, suspended ceiling requirements and test methods* (not part of CE-marking).

2.4 Delivery status

The EPD refers to THERMATEX Acoustic 19 mm which can have variable length and width dimensions.

2.5 Base materials/Ancillary materials

Mineral tile composition:

Name	Value	Unit
Mineral wool	25 - 30	%
Perlite	12 - 15	%
Clay	22 - 25	%
Cellulose fibres	1 - 2	%
Starch	3 - 5	%
others	0	%
Brokes / Dust	27 - 30	%

In addition, the visible side of the mineral tile is laminated with glass fleece (glued) and painted with dispersion paint. The back

side is primed only with a dispersion paint (no glass fleece).

Co-products from other industries and secondary materials are used in production of the rawboard.

On average, reclaimed materials make up 34.7 % of the total, divided as follows:

Pre-consumer materials: 17.0 %

Post-consumer materials: 1.9 %

Co-products (including slag): 15.8 %

This product/article/at least one partial article contains substances listed in the *ECHA-candidate list* (date: 21.01.2025) exceeding 0.1 percentage by mass: No

This product/article/at least one partial article contains other carcinogenic, mutagenic, reprotoxic (CMR) substances in categories 1A or 1B which are not on the *candidate list*, exceeding 0.1 percentage by mass: No

Biocide products were added to this construction product or it has been treated with biocide products (this then concerns a treated product as defined by the (EU) *Ordinance on Biocide Products* No. 528/2012): No

In-can preservatives are used in the production process; however, they are not part of the products and are therefore not within the scope of the *Ordinance on Biocide Products*.

2.6 Manufacture

The mineral tiles are produced in the traditional wet process (wet-felt). The raw materials are mixed with water to form a homogeneous suspension, which is pumped onto a belt conveyor (Fourdrinier). The water is removed mechanically (gravity and vacuum) and by evaporation in the drying oven. As far as possible, the process water is reused. It is treated accordingly and fed back into the process water circuit. Depending on the desired appearance, the panels can be sanded, colour-treated, patterned, eroded or embossed. Production waste and dust are reused in the process in the sense of an internal cycle.

The manufacturing plant is certified according to *ISO 9001*, *ISO 14001*, *ISO 45001* and *ISO 50001*.

2.7 Environment and health during manufacturing

The manufacturer complies with the special German and European regulations for the production of mineral slabs:

- The manufacturing plant is certified according to *ISO 9001*, *ISO 14001*, *ISO 45001* and *ISO 50001*.
- The production has a closed water cycle.
- Production generates almost no waste, resulting blanks, dust and rejects are reused.
- Exclusive use of mineral fibres according to *Regulation (EU) No.1272/2008 Note Q*.
- Prohibition of the production and use of biopersistent fibres (*Ordinance on Hazardous Substances*, Annex II, No. 5).
- Prohibition of placing biopersistent fibres on the market (*Chemicals Prohibition Order*, No.23 of the Annex to §1).
- Not subject to declaration according to *REACH*.

2.8 Product processing/Installation

There are no recognised systemic hazards associated with the installation of ceiling tiles. It is recommended that materials are handled in a manner that minimises dust generation. Workers should wear appropriate personal protective equipment. Equipment such as gloves, goggles and dust masks are

recommended to minimise exposure to dust and prevent skin irritation.

2.9 Packaging

The panels are packaged with cardboard boxes and sealed with transparent polyethylene film. These packages lie on chemically untreated wooden pallets. The pallets are wrapped with polyethylene stretch film. Foil, paper and wood can be recycled in the usual ways.

2.10 Condition of use

When handled properly, the mechanical and structural-physical properties of the mineral tile remain intact throughout its entire service life. Direct contact with water should be avoided due to the water-soluble binding agent starch.

2.11 Environment and health during use

When properly installed, no dust/particles are released during the use phase. For the substance groups formaldehyde, volatile organic compounds (VOCs) and total volatile organic compounds (TVOCs), the limits according to *DIN 18177* are complied with.

2.12 Reference service life

The service life of the mineral tiles (wet-felted) is up to 50 years, depending on the area of use, exposure and state of maintenance. Within the framework of the conditions of use, no ageing effects are to be expected apart from visual discolouration caused by air circulation.

2.13 Extraordinary effects

Fire

The declared products are classified in the fire reaction class A2-s1, d0 according to *EN 13501-1*. This means that they are "non-combustible" according to the German building authority designation (and also many other European countries) with negligible smoke development and no burning drip in the event

of fire.

Fire Reaction

Name	Value
Building material class	A2
Smoke gas development	s1
Burning droplets	d0

Water

In the case of prolonged contact with water, the starch binder dissolves, which can lead to a loss of structure, and if the soluble components are discharged into the sewage treatment plant, they are biodegradable, increasing the chemical oxygen demand (COD) and the biological oxygen demand (BOD).

Mechanical destruction

The mineral slabs (wet-felt) can be broken by hand and also damaged superficially, which can result in minor dust formation.

2.14 Re-use phase

If the panels are removed properly, they can be reinstalled. In case of minor damage, the slabs can be reused as cut-to-size tiles. Mineral tiles can be returned to the manufacturing process if they are of the correct type and have sufficient material quality; they can be recycled up to 100 %.

2.15 Disposal

The waste code number of production residues for mineral tiles according to the *AVV, German List of Wastes Ordinance* is 10 11 03, the waste code number for construction site waste (offcuts) is 17 06 04. If the tiles are not recycled as described in 2.14., they are disposed of in a landfill.

2.16 Further information

Further information at www.knauf.com

3. LCA: Calculation rules

3.1 Declared Unit

This EPD refers to a declared unit of 1 m² THERMATEX Acoustic mineral ceiling tiles with a surface weight of 5.23 kg/m² and a thickness of 19 mm.

Declared Unit

Name	Value	Unit
Declared unit	1	m ²
Grammage	5.23	kg/m ²
Layer thickness	0.019	m

The ceiling tiles are produced at the Knauf Ceiling Solutions production site in Grafenau, Germany.

As the declaration refers to a specific product, no averages had to be calculated.

3.2 System boundary

The life cycle assessment of the mineral ceiling tiles includes a cradle-to-gate analysis of the products' environmental impacts with modules C1–C4 and module D (A1–A3, + C + D). Subsequent life cycle phases are part of the analysis:

Module A1–A3 | Production stage

The production stage includes the upstream burdens of raw material supply, their transport and the manufacturing plant of Knauf Ceiling Solutions located in Grafenau (Germany). Mineral ceiling tiles are produced in the wet-felt process. Main raw material inputs, therefore, refer to mineral wool, perlite, clay and starch. The production site is supplied with electricity from the

German power grid (considered based on the German residual mix: GWP-total = 0.9 kg CO₂ e/kWh) and thermal energy from natural gas. Also, the packaging of the products is considered.

Module C1 | Deconstruction and demolition

Disassembly of the product is done either manually or using smaller tools. Referring energy demand is considered to be negligible.

Modul C2 | Transport to disposal

The transport to the disposal of the material is estimated, declaring a 50 km radius to the landfill. In reality, this scenario may vary depending on the actual location of deconstruction and referring waste treatment.

Module C3 | Waste processing

The declared scenario assumes landfilling of the product. Referring environmental impacts are accounted for in module C4.

Module C4 | Disposal

Module C4 refers to the emissions from the disposal of the mineral ceiling tiles. The chosen scenario, therefore, includes the environmental burdens of landfilling of the product. There are no benefits and loads in module D.

Module D | Benefits and loads beyond the system boundary

The declared scenario assumes landfilling of the product. Referring environmental impacts are accounted for in module

C4.

3.3 Estimates and assumptions

Assumptions and approximations are applied in case of a lack of representative data. All assumptions and approximations are documented precisely and represent a best-guess representation of reality. In case of uncertainty, a conservative approach is chosen.

3.4 Cut-off criteria

The LCA model covers all available input and output flows, which can be represented based on robust data. Data gaps are filled with conservative assumptions from average data (when available) or with generic data and are documented accordingly. Only data with a contribution lower than 1 % were cut off. Thus, no data were neglected, of which a substantial impact is to be expected. All relevant data were collected comprehensively. Cut-off material and energy flows were chosen carefully based on their expected quantitative contribution as well as potential environmental impacts. Thus, it can be assumed that the sum of all neglected input flows does not account for more than 5 % of the total material, water and energy flows.

3.5 Background data

This study uses generic background data for the evaluation of upstream environmental impacts from *MLC 2024.2* database in the *LCA FE*-software version 10.

3.6 Data quality

Data collection is based on product-specific questionnaires. It follows an iterative process clarifying questions via e-mail, telephone calls or in personal/web meetings. Intensive discussions between Knauf Ceiling Solutions and Daxner & Merl result in an accurate mapping of product-related material and energy flows. This leads to a high quality of foreground data collected. Data collection relies on a consistent process according to *ISO 14044*.

The technological, geographical and time-related representativeness of the database was kept in mind when selecting background data. Whenever specific data were missing, either generic datasets or representative average data were used instead. The implemented *MLC* background

datasets refer to the latest versions available and are carefully chosen.

3.7 Period under review

Foreground data were collected in the 2023 production year, and the data are based on the volumes produced on an annual basis.

3.8 Geographic Representativeness

Land or region, in which the declared product system is manufactured, used or handled at the end of the product's lifespan: Germany

3.9 Allocation

All information for the allocation of given material and energy flows is based on the ERP-systems of the production site. Annual input quantities are only available for the overall production site. Thus, the calculation of specific input quantities for the raw board production is based on their respective recipe. In addition, product-specific application rates of backcoat and primer were available. The total annual energy consumption as well as waste quantities were broken down to the product under study based on their production share (produced square meters).

Knauf Ceiling Solutions uses waste paper and waste fibreglass as secondary material. Waste paper reaches its end of waste status after sorting of the paper, waste fibreglass after sorting and grinding. As a result, the upstream supply chain of waste paper and waste fibre glass are considered burden-free. The system boundary for secondary raw materials defined in *EN 15804* applies.

3.10 Comparability

Basically, a comparison or an evaluation of EPD data is only possible if all the data sets to be compared were created according to *EN 15804* and the building context, respectively the product-specific characteristics of performance, are taken into account.

The *MLC 2024.2* background database (former GaBi) in the *LCA FE*-software version 10 was used to calculate the LCA. This EPD was created based on an LCA-tool.

4. LCA: Scenarios and additional technical information

Characteristic product properties of biogenic carbon

The biogenic carbon content quantifies the amount of biogenic carbon in the declared product.

Information on the description of the biogenic carbon content at the factory gate

Name	Value	Unit
Biogenic carbon content in product	0.16	kg C
Biogenic carbon content in accompanying packaging	0.06	kg C

Note: 1 kg of biogenic carbon is equivalent to 44/12 kg of CO₂.

As the End-of-Life of the product packaging is not declared in module A5, its carbon uptake is not considered in module A1–

A3.

Assembly (A5)

The End-of-Life of the product packaging is not declared in module A5.

Name	Value	Unit
Packaging (cardboard)	0.047	kg/m ²
Packaging (pallets)	0.088	kg/m ²
Packaging (polyethylene foil)	0.004	kg/m ²

End-of-Life (C1–4)

Name	Value	Unit
Collected separately waste type	5.23	kg
Landfilling	5.23	kg

5. LCA: Results

The following table contains the LCA results for a declared unit of 1 m² mineral ceiling tile [characterisation model EF 3.1].

DESCRIPTION OF THE SYSTEM BOUNDARY (X = INCLUDED IN LCA; MND = MODULE OR INDICATOR NOT DECLARED; MNR = MODULE NOT RELEVANT)

Product stage			Construction process stage		Use stage							End of life stage				Benefits and loads beyond the system boundaries
Raw material supply	Transport	Manufacturing	Transport from the gate to the site	Assembly	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction demolition	Transport	Waste processing	Disposal	Reuse-Recovery-Recycling-potential
A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4	D
X	X	X	MND	MND	MND	MND	MNR	MNR	MNR	MND	MND	X	X	X	X	X

RESULTS OF THE LCA - ENVIRONMENTAL IMPACT according to EN 15804+A2: 1 m² THERMATEX Acoustic mineral ceiling tiles (5.23 kg/m²)

Parameter	Unit	A1-A3	C1	C2	C3	C4	D
Global Warming Potential total (GWP-total)	kg CO ₂ eq	4.6E+00	0	2E-02	0	6.7E-01	0
Global Warming Potential fossil fuels (GWP-fossil)	kg CO ₂ eq	5.2E+00	0	2E-02	0	7.8E-02	0
Global Warming Potential biogenic (GWP-biogenic)	kg CO ₂ eq	-5.8E-01	0	4.8E-05	0	5.9E-01	0
Global Warming Potential luluc (GWP-luluc)	kg CO ₂ eq	4.7E-03	0	3.4E-04	0	4.7E-04	0
Depletion potential of the stratospheric ozone layer (ODP)	kg CFC11 eq	2.4E-10	0	2.9E-15	0	2.1E-13	0
Acidification potential of land and water (AP)	mol H ⁺ eq	1.6E-02	0	2.6E-05	0	5.6E-04	0
Eutrophication potential aquatic freshwater (EP-freshwater)	kg P eq	8.9E-05	0	8.5E-08	0	1.8E-07	0
Eutrophication potential aquatic marine (EP-marine)	kg N eq	3.9E-03	0	9.7E-06	0	1.4E-04	0
Eutrophication potential terrestrial (EP-terrestrial)	mol N eq	5.2E-02	0	1.1E-04	0	1.6E-03	0
Formation potential of tropospheric ozone photochemical oxidants (POCP)	kg NMVOC eq	7.9E-03	0	2.7E-05	0	4.4E-04	0
Abiotic depletion potential for non fossil resources (ADPE)	kg Sb eq	2E-06	0	1.7E-09	0	5.1E-09	0
Abiotic depletion potential for fossil resources (ADPF)	MJ	7.6E+01	0	2.6E-01	0	1E+00	0
Water use (WDP)	m ³ world eq deprived	2.1E-01	0	3.1E-04	0	9E-03	0

RESULTS OF THE LCA - INDICATORS TO DESCRIBE RESOURCE USE according to EN 15804+A2: 1 m² THERMATEX Acoustic mineral ceiling tiles (5.23 kg/m²)

Parameter	Unit	A1-A3	C1	C2	C3	C4	D
Renewable primary energy as energy carrier (PERE)	MJ	2.5E+00	0	2.3E-02	0	1.8E-01	0
Renewable primary energy resources as material utilization (PERM)	MJ	4.5E+00	0	0	0	0	0
Total use of renewable primary energy resources (PERT)	MJ	7.1E+00	0	2.3E-02	0	1.8E-01	0
Non renewable primary energy as energy carrier (PENRE)	MJ	7.6E+01	0	2.6E-01	0	1E+00	0
Non renewable primary energy as material utilization (PENRM)	MJ	1.9E-01	0	0	0	0	0
Total use of non renewable primary energy resources (PENRT)	MJ	7.6E+01	0	2.6E-01	0	1E+00	0
Use of secondary material (SM)	kg	8.2E-01	0	0	0	0	0
Use of renewable secondary fuels (RSF)	MJ	0	0	0	0	0	0
Use of non renewable secondary fuels (NRSF)	MJ	0	0	0	0	0	0
Use of net fresh water (FW)	m ³	1.3E-02	0	2.5E-05	0	2.7E-04	0

RESULTS OF THE LCA – WASTE CATEGORIES AND OUTPUT FLOWS according to EN 15804+A2: 1 m² THERMATEX Acoustic mineral ceiling tiles (5.23 kg/m²)

Parameter	Unit	A1-A3	C1	C2	C3	C4	D
Hazardous waste disposed (HWD)	kg	7.4E-06	0	1E-11	0	2.6E-10	0
Non hazardous waste disposed (NHWD)	kg	5.1E-01	0	4.3E-05	0	5.2E+00	0
Radioactive waste disposed (RWD)	kg	1.2E-03	0	4.8E-07	0	1.1E-05	0
Components for re-use (CRU)	kg	0	0	0	0	0	0
Materials for recycling (MFR)	kg	0	0	0	0	0	0
Materials for energy recovery (MER)	kg	0	0	0	0	0	0
Exported electrical energy (EEE)	MJ	0	0	0	0	0	0
Exported thermal energy (EET)	MJ	0	0	0	0	0	0

RESULTS OF THE LCA – additional impact categories according to EN 15804+A2-optional: 1 m² THERMATEX Acoustic mineral ceiling tiles (5.23 kg/m²)

Parameter	Unit	A1-A3	C1	C2	C3	C4	D
Incidence of disease due to PM emissions (PM)	Disease	1.4E-07	0	2.6E-10	0	7E-09	0

	incidence						
Human exposure efficiency relative to U235 (IR)	kBq U235 eq	1.5E-01	0	7E-05	0	1.3E-03	0
Comparative toxic unit for ecosystems (ETP-fw)	CTUe	1.5E+01	0	2E-01	0	5.9E-01	0
Comparative toxic unit for humans (carcinogenic) (HTP-c)	CTUh	1.8E-09	0	3.9E-12	0	1.4E-11	0
Comparative toxic unit for humans (noncarcinogenic) (HTP-nc)	CTUh	3.1E-08	0	1.8E-10	0	5.4E-10	0
Soil quality index (SQP)	SQP	3.9E+01	0	1.3E-01	0	2.8E-01	0

Disclaimer 1 – for the indicator 'Potential Human exposure efficiency relative to U235'.

This impact category deals mainly with the eventual impact of low-dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure or radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, radon and from some construction materials is also not measured by this indicator.


Disclaimer 2 – for the indicators 'abiotic depletion potential for non-fossil resources', 'abiotic depletion potential for fossil resources', 'water (user) deprivation potential, deprivation-weighted water consumption', 'potential comparative toxic unit for ecosystems', 'potential comparative toxic unit for humans – cancerogenic', 'Potential comparative toxic unit for humans - not cancerogenic', 'potential soil quality index'. The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high as there is limited experience with the indicator.

6. LCA: Interpretation

The LCA result tables presented in chapter 5 refer to product specific results of the declared mineral ceiling tile produced at

one site operated by Knauf Ceiling Solutions.

Thermatex Acoustic



The comparison of the products' life cycle phases shows a clear dominance of the production phase (modules A1-A3) in all environmental impact categories. Environmental impacts in module C4 represent the landfilling of the material, including the emission of the biogenic carbon remaining in it. The emission of biogenic greenhouse gases (GWP-biogenic) confirms the correct consideration of the biogenic carbon in the

model.

The upstream supply chain of the thermal energy supply for the drying ovens plays a dominant role in the carbon footprint of the products.

In addition, the supply chain of the components used for the raw board accounts for another relevant share of the impact.

7. Requisite evidence

7.1 Radioactivity

Measurements of radioactivity did not reveal any evidence of artificial radioactivity outside the natural background radiation. Measuring point: TÜV Süd Industrie Service

Test Number: G 7299 002

Testing Date: 23.06.2021

7.2 Biopersistence

The mineral wool used for the production of the panels is

biosoluble and, according to *EU Regulation 1272/2008/EC*, is to be assessed as free of suspected cancer. The "*RAL Mineral Wool Quality Seal*" monitors and guarantees the quality of the wool used.

The production and use of non-exempt fibres is prohibited by the *Ordinance on Hazardous Substances* and the *Chemicals Prohibition Ordinance*.

7.3 VOC emissions

Measuring point: *Eurofins Product Testing A/S*

Indoor Air Comfort GOLD Certificate

Number: IACG-426-01-01-2024

Issue Date: 01 March 2024

Test basis: *EN 16516*

AgBB Overview (28 days)

Name	Value	Unit
TVOC (C6 - C16)	92	µg/m ³
Sum SVOC (C16 - C22)	< 5	µg/m ³
R (dimensionless)	0.056	
VOC without NIK	< 5	µg/m ³
Carcinogenic substances	< 1	µg/m ³

8. References

Standards

DIN 18177

DIN 18177:2012, Mineral tiles manufactured in the factory by the wet felt process - Characteristic values and test methods.

EN 13501-1

DIN EN 13501-1:2019, Classification of construction products and building elements according to their reaction to fire, Part 1: Classification with the results of tests on the reaction to fire of construction products.

EN 13964

DIN EN 13964:2014, Suspended ceilings - Requirements and test methods.

EN 15804

DIN EN 15804:2012+A2:2019, Sustainability of construction works - Environmental product declarations - Core rules for the product category of construction products.

EN 16516

DIN EN 16516:2020-10, Construction products: Assessment of release of dangerous substances - Determination of emissions into indoor air.

ISO 354

DIN EN ISO 354:2003-12, Acoustics - Measurement of sound absorption in reverberant rooms.

ISO 717-1

DIN EN ISO 717-1:2013-06, Acoustics - Assessment of sound insulation in buildings and of building elements - Part 1: Airborne sound insulation.

ISO 9001

DIN EN ISO 9001:2015-11, Quality management systems - Requirements.

ISO 10848-2

DIN EN ISO 10848-2:2006-08, Acoustics - Measurement of airborne and impact sound transmission between adjacent rooms in test stands - Part 2: Application to lightweight components where the connection has a minor influence.

ISO 11654

DIN EN ISO 11654:1997-07, Acoustics - Sound absorbers for use in buildings - Evaluation of sound absorption.

ISO 14001

DIN EN ISO 14001:2015-11, Environmental management systems - Requirements with guidance for use.

ISO 14025

DIN EN ISO 14025:2011-10, Environmental labels and

declarations — Type III environmental declarations — Principles and procedures.

ISO 14044

DIN EN ISO 14044:2006-10, Environmental management – Life cycle assessment – Requirements and guidelines.

EN 16516

DIN EN 16516:2020-10, Construction products: Assessment of release of dangerous substances - Determination of emissions into indoor air.

ISO 45001

DIN ISO 45001:2018-06, Occupational health and safety management systems - Requirements with guidance for use.

ISO 50001

DIN EN ISO 50001:2011-12, Energy management systems - Requirements with guidance for use.

Further References

AgBB

Ausschuss zur gesundheitlichen Bewertung von Bauprodukten (AgBB) (Committee for health-related evaluation of building products): Vorgehensweise bei der gesundheitlichen Bewertung der Emissionen von flüchtigen organischen Verbindungen (VOC und SVOC) aus Bauprodukten.

AVV, German List of Wastes Ordinance

Regulation on the European Waste List.

Chemicals Prohibition Ordinance

Chemicals Prohibition Ordinance (German designation: Chemikalien-Verbotsverordnung – ChemVerbotsV) of 20 January 2017 (Federal Law Gazette I p. 94; 2018 I p. 1389), last amended by Article 300 of the Ordinance of 19 June 2020 (Federal Law Gazette I p. 1328).

ECHA-candidate list

List of substances of very high concern (SVHC) for authorisation (ECHA Candidate List), 21.01.2025, published under Article 59(10) of REACH. Helsinki: European Chemicals Agency.

Eurofins Product Testing A/S

Test report: VOC emission test report Indoor Air Comfort GOLD (01.03.2024), Number: IACG-426-01-01-2024.

IBU 2021

General instructions for the EPD program of Institut Bauen und Umwelt e.V. (IBU). Version 2.0, Berlin: Institut Bauen und Umwelt e.V., 2021. www.ibu-epd.com

LCA FE

LCA FE 10, LCA for Experts Software System and Database for Life Cycle Engineering. Version 10.7.1.28. Sphera, 1992-2023.

MLC

MLC 2024.2, Database for Life Cycle Engineering implemented in LCA for Experts software system. DB 2024.2. Sphera, 1992-2024. Available at: <https://lcadatabase.sphera.com/>.

Ordinance on Biocide Products

Regulation (EU) No 528/2012 of the European Parliament and of the Council of 22 May 2012 concerning the making available on the market and use of biocidal products.

Ordinance on Hazardous Substances

Ordinance on Hazardous Substances, of 26 November 2010 (Federal Law Gazette I p. 1643, 1644), last amended by Article 148 of the Law of 29 March 2017 (Federal Law Gazette I p. 626).

PCR Part A

Product category rules for buildingrelated products and services. Part A: Calculation rules for the life cycle assessment and requirements for the project report in accordance with EN 15804+A2:2019. Version 1.4. Berlin: Institut Bauen und Umwelt e.V. (eds.), 2024.

PCR: Mineral panels

Institut Bauen und Umwelt e.V. (IBU), 2021. Product Category Rules for Building-Related Products and Services. Part B:

Requirements on the EPD for Mineral panels. 08.2021.

RAL Mineral Wool Quality Seal

GGM members with the right to use the RAL quality mark including plants and fibre types, as of January 2021.

REACH

Regulation (EC) No 1907/2006 of the European Parliament and Council from 18 December 2006, Regulation concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH).

Regulation (EU) Nr. 305/2011(CPR)

Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC Text with EEA relevance.

Regulation (EU) Nr.1272/2008

Regulation (EC) No 1272/2008 of the European Parliament and of the Council of 16 December 2008 on classification, labelling and packaging of substances and mixtures, amending and repealing Directives 67/548/EEC and 1999/45/EC, and amending Regulation (EC) No 1907/2006.

TÜV Süd Industrie Service

TÜV Strahlenmesslabor. IS-ETS1-MUC/er.



Publisher

Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

+49 (0)30 3087748- 0
info@ibu-epd.com
www.ibu-epd.com



Programme holder

Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

+49 (0)30 3087748- 0
info@ibu-epd.com
www.ibu-epd.com



Author of the Life Cycle Assessment

Daxner & Merl GmbH
Schleifmühlgasse 13/24
1040 Wien
Austria

+43 676 849477826
office@daxner-merl.com
www.daxner-merl.com



Owner of the Declaration

Knauf Ceiling Solutions GmbH & Co. KG
Elsenthal 15
94481 Grafenau
Germany

0049 8552 422 0
ceiling.solutions@knauf.com
www.knaufceilingsolutions.com